



Fig. 10.3 (a) Computed fraction solid vs. temperature curves for an Al-4.5 wt% Cu alloy, using the lever rule and the Gulliver-Scheil equation. The experimental data were obtained by DTA experiments. [8] (b) The corresponding microsegregation patterns for the two solidification models.

Copyright 2016 EPFL Press. This figure has been reproduced from *Solidification*, by J.A. Dantzig and M. Rappaz, for instructional purposes. For other uses, please contact the authors and the EPFL Press for written permission.