



Fig. 12.19 Temporal evolution of the radius of the pore for three different pore densities. The other parameters are: $D_{\ell H} = 10^{-8} \text{ m}^2 \text{ s}^{-1}$, $C_{H0} = 0.8$ and $C_{H\ell}^{eq}(p_\ell = 10^5 \text{ Pa}) = 0.3 \text{ cc}_{\text{STP}}/100 \text{ g}$, pore nucleation radius $R_{pn} = 10 \text{ } \mu\text{m}$, $\gamma_{\ell g} = 0.9 \text{ J m}^{-2}$ and $T = 933 \text{ K}$.

Copyright 2016 EPFL Press. This figure has been reproduced from *Solidification*, by J.A. Dantzig and M. Rappaz, for instructional purposes. For other uses, please contact the authors and the EPFL Press for written permission.